

## الملخص

تم في هذه الدراسة تحضير البوليمر الموصل بولي (أورثو-أنسدين) باستخدام طريقة البلمرة الكيميائية وتشويب هذا البوليمر بحامض الهيدروكلوريك (HCL). وجد انه يمكن إزالة التشويب من الأغشية البوليمرية المحضرة بواسطة غمرها في سائل الامونيا و بفترات زمنية محددة. تم ترسيب (POA-HCL),(POA) على قواعد من الزجاج والالمنيوم و الحديد المقاوم للصدأ (stainless steel) باستخدام تقنيتي الصب Casting و الطلاء البرمي Spin coating.

شخصت الأغشية البوليمرية المحضرة باستخدام طيف (الأشعة تحت الحمراء FT-IR) لمعرفة المجاميع الفعالة للأواصر الكيميائية.

تمت دراسة الخواص البصرية للأغشية المحضرة التي تضمنت حساب معامل الامتصاص  $\alpha$ ، فجوة الطاقة Eg، معامل الانكسار n، كما تم حساب الثوابت البصرية المتمثلة بطاقة التفريق Ed وطاقة التذبذب الاحادي E0 والتأثرية اللاخطية من المرتبة الثالثة X(3) ومعاملات الزخم M-3, M-1.

من خلال دراسة الخواص الكهربائية أختبرت ميكانيكية التوصيل الكهربائي وكانت من نوع شوتكي ووجد أن هذه الاغشية تتحرف عن السلوك الاومي عند الفولتية الاعلى من 6 V.

تم دراسة تأثير درجة الحرارة على التوصيلية الكهربائية لأغشية POA ، وقد بينت الدراسة أن التوصيلية تزداد مع زيادة درجة الحرارة حيث تكون الاغشية ذات معامل حراري سالب وهي إحدى الصفات التي تمتاز بها أشباه الموصلات، أما أغشية POA-HCL فأنها تسلك سلوك معدني حيث وجد أن التوصيلية تقل بارتفاع درجة الحرارة. تم دراسة تأثير التشويب على التوصيلية الكهربائية حيث أزدادت من  $2 \times 10^{-11}$  S/cm الى  $5 \times 10^{-9}$  S/cm عند التشويب ب HCL. كذلك فإن الدراسة بينت ان طاقة التنشيط تقل 0.89 eV الى 0.53 eV عند تشويب البوليمر.

تم تصنيع ثنائي شوتكي باستخدام (Al/POA-HCL/St, Al/POA/St) وتمت دراسة الخصائص الكهربائية لهذا الثنائي حيث تم حساب ارتفاع حاجز الجهد  $\phi_{bi}$  ومقاومة التوالي  $R_s$  وعامل الجودة والتي كانت تساوي  $(1.002 \pm 3.4) \times 10^4 \Omega$ ، (eV)، على التوالي أما عند تشويب البوليمر فقد تحسنت قيم الثوابت الكهربائية لثنائي شوتكي لتكون  $\phi_{bi} = 0.837$  eV،  $R_s = 0.3285710 \text{ M}\Omega$ ،  $n = 2.29$ .

## Abstract

as it is found that the dope can be removed from prepared polymeric thin films by immersing it in Ammonia solution within specific timing intervals. The (POA) and (POA-HCl) were deposited on glass, aluminum, stainless steel substrates using casting method and spin coating technique. The prepared polymeric films were analyzed using FT-IR to identify the active chemical bonding groups.

Optical properties of the prepared films were studied including calculating absorption coefficients ( $\alpha$ ), energy gap  $E_g$ , Refraction index ( $n$ ) and also calculated optical constants represented by dispersion energy  $E_d$ , single Oscillator Energy ( $E_0$ ), the non-linear optical susceptibility  $X(3)$  and Moments of Dielectric constants ( $M-1$ ,  $M-3$ ).

The mechanism of the polymer were studied through the conductivity of POA films and its found that the schottky mechanism is dominated. These films are deviated from Ohmic behavior at in the range above of 6 V.

Studying the effect of temperature on the electrical conductivity of POA films showed that, the conductivity is increased linearly with the raise of temperature. Its found that that the (POA) films have a negative thermal coefficients (i.e) The films behavior as semiconductors. while the (POA-HCL) films takes metal behavior so that conductivity is lessen upon increasing temperature.

Doping effect on the electrical conductivity has been studied so that it is increased from  $2 \times 10^{-11}$  S/cm to  $5 \times 10^{-9}$  S/cm upon doping with HCl. Also, the study showed that the activation energy is decreased from 0.89 eV into 0.53 eV upon doping polymer.

Diode Schottky is fabricated using (Al-POA-HCl/St, Al/POA/St) and studied its electrical properties calculating the raise of this potential barrier  $\phi_{bi}$  and series resistance  $R_s$  the quality factor equaled to (1.002 eV), (400 M $\Omega$ ), (3.4), respectively. While upon doping polymer, the constant electrical values of Diode Schottky were improved to be  $\phi_{bi}=0.837$  eV,  $R_s=0.3285710$  M $\Omega$ ,  $n=2.29$ .